

# INFORMATION SHEET

## POWDER COATING



Claire Works,  
Anders,  
Lichfield Road Industrial Estate,  
Tamworth, B79 7TA.  
Telephone (01827) 55777  
Facsimile (01827) 53713  
www.thermaset.co.uk

### Chemical Resistance

	Epoxy	Epoxy-Polyester	Polyester
Fresh water	+	+	+
Salt water	+	+	+
Sulphuric acid 10%	+	+	+
Sulphuric acid. Conc.	-	-	-
Hydrochloric acid 10%	+	+	+
Hydrochloric acid. Conc.	±	±	±
Nitric acid 10%	±	-	-
Nitric acid. Conc.	-	-	-
Phosphoric acid 50%	+	+	+
Caustic soda 10%	+	±	+
Caustic soda 30%	+	-	±
Ammonia 10%	±	±	±
Acetic acid 10%	+	+	+
Tartaric acid 5%	+	+	+
Lactic acid 10%	+	+	+
Ethyl alcohol 96%	+	+	+
Methyl ethyl ketone	±	-	-
Acetone	-	±	-
Petroleum	+	+	+
Trichloroethylene	-	-	-
Glycerine	+	+	+
Triethylamine	+	+	+
Toluene	+	±	±
Methyl chloride	-	-	-
Hydrogen peroxide 3%	±	-	-
Cyclohexanone	-	-	-
Linseed oil	+	+	+
Penetrating oil	+	+	+

Resistance tests by immersion at 20°C

+ Resistance good      ± Resistance limited      - Resistance poor

Data quoted is typical but may vary from product to product.

Our data sheets and sales literature are issued for the purpose of supplying general product information. In view of the variation of conditions under which products may be used or this information may be applied, we cannot accept responsibility for loss, damage or accident of any nature (or infringement of patent rights) which may result from the use or application of the information or the products. For specific confirmation of any details in the product information or use and application please apply to the company in writing.