

## POWDER COATING

### Epoxy-Polyester Post-forming Powder Coatings

The information given in this data sheet is generic for Thermaset Limited Epoxy-Polyester Post-forming Powder Coatings.

**Date:** 06/12/2018

**Product Code:** Generic sheet for the series

#### Product Description:

Thermaset Limited offer a range of highly flexible powder coatings designed for interior use. This range is specially formulated on selected polyester and epoxy resins and pigments to give a tough decorative finish with increased mar, scuff and abrasion resistance and superior flexibility and substrate adhesion to allow items to be formed to shape after powder coating.

#### Colours Available:

Thermaset's Epoxy-Polyester Post-forming Powder Coatings can be matched to customer supplied samples or to many of the RAL and BS colour ranges.

#### Substrate Preparation:

For maximum adhesion the substrate must be thoroughly cleaned of grease, rust etc. by shot blasting, solvent or chemical degreasing. For maximum protection it is essential to pretreat the substrate prior to the application of Thermaset Limited Epoxy-Polyester Post-forming Powder Coatings.

Aluminium components should receive a full multi-stage chromate conversion coating or similar chrome-free pretreatment to clean and prepare the substrate. Detailed advice should be sought from the pretreatment supplier.

Galvanized steel requires multi-stage pretreatment with either zinc phosphate or chromate conversion.

Depending on the type of galvanizing, degassing or use of anti-bubbling additives may be required. Detailed advice should be sought from the pretreatment supplier.

Ferrous substrates require iron or zinc phosphate pretreatment. Detailed advice should be sought from the pretreatment supplier.

#### Application:

Thermaset Limited Epoxy-Polyester Post-forming Powder Coatings can be applied by manual or automatic electrostatic spray equipment, an even dry film thickness of 60 microns is recommended.

#### Powder Properties:

Type	Thermosetting hybrid epoxy polyester resin system.
60° Gloss (EN ISO 2813)	Gloss Semi-gloss Matt
Specific Gravity	1.3-1.8 depending on colour
Particle size	Suitable for electrostatic spray
Stoving schedule	See box label for recommended curing conditions. Typical values are; 10 minutes @ 180°C peak metal temperature
Storage and shelf life	12 months when stored in cool (below 25°C) dry conditions. Open boxes must be resealed.

## POWDER COATING

### Epoxy-Polyester Post-forming Powder Coatings

#### Test Conditions:

Unless otherwise specified, all tests have been carried out under laboratory conditions on 0.8mm degreased and zinc phosphated panels and are given for guidance only. Actual product performance will depend on the circumstances under which the product is used. A powder coating dry film thickness of 60-70 microns was used.

#### Mechanical Tests:

Flexibility (0.25mm tinplate)	ISO 1519	Pass minimum 2mm (limit of equipment)
Buchholz Hardness	ISO 2815	Pass minimum 80
Impact	ISO 6272-2	Pass minimum 2.5Nm
Erichsen cupping (0.25mm tinplate)	ISO 1520	Pass minimum 9mm (limit of substrate)
Adhesion (2mm cross hatch)	ISO 2409	Pass Gt 0
Scratch Resistance	ISO 1518-1	Pass 4 Kg

#### Chemical Tests:

Humidity	ISO 6270	Pass 1000 hours.
Boiling water	2 hours	No defects or detachments.
Neutral Salt Fog	ISO 9227	Pass 250 hours, < 2mm creep from scribe.
Mortar resistance	EN 12206-1	Easy to remove, no staining.

#### Exterior Durability:

Not designed for long term exterior exposure. Some chalking and loss of gloss can be expected after 3-6 months continuous outdoor exposure.

#### Chemical Resistance:

Generally good resistance to acids, alkalis and oil at normal temperatures.

#### Health and Safety Precautions:

This product is intended for use only by professional applicators in industrial environments. Consult the relevant Material Safety Data Sheet available from Thermaset.

#### Restrictions of Hazardous Substances (RoHS3):

Thermaset Limited Epoxy-Polyester Post-forming Powder Coatings range is suitable for use on items covered by Restriction of the Use of Certain Hazardous Substances in Electrical and Electronic Equipment Regulations 2012 (Directive 11/65/EU, RoHS3). Products in the range contain none (or less than the maximum allowed amount) of the following restricted chemicals:-

Lead, Mercury, Cadmium, Hexavalent Chromium or their compounds.

Poly-brominated biphenyl (PBB) or Poly-brominated diphenyl ether (PBDE) flame retardants.

Bis(2-ethylhexyl) phthalate (DEHP), Benzyl butyl phthalate (BBP), Dibutyl phthalate (DBP),

Diisobutyl phthalate (DIBP)

Our data sheets and sales literature are issued for the purpose of supplying product information. The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfil the demands set out in the local rules and legislation. Always read the Material Safety Data Sheet and the Technical Data Sheet for the product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advices given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous improvement. It is the user's responsibility to verify that this data sheet is current prior to using the product.